

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : F23D 14/16	A1	(11) International Publication Number: WO 99/18393 (43) International Publication Date: 15 April 1999 (15.04.99)
(21) International Application Number: PCT/EP98/06245 (22) International Filing Date: 29 September 1998 (29.09.98) (30) Priority Data: 9700792 2 October 1997 (02.10.97) BE (71) Applicant (for all designated States except US): N.V. BEKAERT S.A. [BE/BE]; Bekaertstraat 2, B-8550 Zwevegem (BE). (72) Inventors; and (75) Inventors/Applicants (for US only): LAMBERT, Eddy [BE/BE]; Veemeersstraat 16, B-8540 Deerlijk (BE). DEWAEGHENEIRE, Gabriel [BE/BE]; Demeesterstraat 2 - I, Bus 6, B-8550 Zwevegem (BE). (74) Common Representatives: MESSELY, Marc et al.; N.V. Bekaert S.A., Bekaertstraat 2, B-8550 Zwevegem (BE).		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: BURNER MEMBRANE COMPRISING A NEEDED METAL FIBRE WEB		
(57) Abstract The invention relates to a burner membrane comprising at least one layer consisting of a compressed, needled fibre web with a porosity of between 60 % and 95 %, and that is constructed of heat-resistant stainless steel fibres. Moreover, the invention relates to a method for its manufacture, comprising the steps of providing a fibre web composed of heat-resistant stainless steel fibres, needling the fibre web, and compressing the needled fibre web to the desired porosity.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**BURNER MEMBRANE COMPRISING A NEEDED METAL
FIBRE WEB**

Field of the invention.

5 The invention relates to a burner membrane comprising heat-resistant stainless steel fibres.

Background of the invention.

10 A number of types of burner membranes composed of heat-resistant stainless steel fibres are already known, comprising, for example, a sintered metal fibre web or a knitted metal fibre structure.

15 However, the use of a sintered web as a burner membrane, as described in European patent EP 0157432 (priority date : 1984), displays a few drawbacks.

20 For example, the porosity of a sintered metal fibre web as such is often insufficiently homogeneous, so that the flow of gas through the membrane is not sufficiently uniform. The axial temperature gradient that is established through the burner membrane during burning results in a non-homogeneous thermal-expansion and mechanical [stresses]. After a number of heating and cooling cycles, these stresses can lead to cracks or fissures in the

25 membrane. These drawbacks can in part be dealt with by providing the surface of the burner membrane with a regular pattern of perforations or a grid-like pattern of grooves, such as described respectively in PCT patent application WO 93/18342 (priority date : 1992) and European patent EP 0390255 (priority date : 1989), both submitted by the applicant.

30 Furthermore, a burner membrane composed of a sintered metal fibre web is deformable only to a limited extent, which also constitutes a significant drawback.

Knitted membranes composed of metal fibres, as described in PCT patent application WO 97/04152 (priority date : 1995) of the applicant, deal to a significant extent with the aforementioned drawbacks, but their construction is relatively complicated.

Summary of the invention.

It is the object of the invention to deal with the drawbacks of the aforementioned types of burner membranes and to provide a metal fibre burner membrane that possesses a high and nearly homogeneous porosity, and that is to a large extent deformable. Moreover, the membrane possesses a considerable mechanical cohesion and strength, and can be fabricated in an inexpensive and simple manner.

To this end, the invention provides a burner membrane comprising at least one layer consisting of a compressed, needled fibre web composed of heat-resistant stainless steel fibres. The porosity of the burner membrane is between 60 % and 95 %.

The heat-resistant stainless steel fibre bundles that are incorporated in the fibre web and that are composed, for example, of Fecralloy®, can be obtained by means of the technique of bundled drawing, as described in US patent 3379000, or by shaving the rolled edge of a roll of metal foil, as described in US patent 4930199, or directly from the melt, for example by extrusion, as described in US patent 5524704.

With respect to the present invention, the better fibres are those obtained by shaving the rolled edge of a roll of metal foil, as

described in US patent 4930199. The reason is that they have not a round transversal cross-section, which allows them to be intertwined to a more coherent structure during the needling operation.

5

The steel fibres have an equivalent diameter of between 5 μm and 150 μm , by preference between 10 μm and 50 μm . The equivalent diameter is here defined as the diameter of an imaginary round fibre having the same cross-section as that of the real fibre in question.

10

Apart from this, steel wool can also be used to fabricate the fibre web.

15

The burner membrane according to the invention can be obtained by and the sintering step of the web can be avoided by :

- a) providing a fibre web composed of heat-resistant stainless steel fibres, whether multi-layered or not ;
- b) needling the fibre web ;
- c) compressing the needled fibre web to the desired porosity, for example by means of a roller or press operation.

20

Compressing is done to give the desired stability to the membrane. The needled fibre web may be compressed to such a degree that cold weldings are just avoided.

25

A correspondingly formed burner membrane can be obtained by needling a flat, tubular, cylindrical or conical metal fibre web.

30

The burner membrane according to the invention has a nearly homogeneous porosity, which is between 60 % and 95%, and by

preference between 80 % and 95 %. This makes it possible to utilize large and uniform gas flows.

5 The weight of the burner membrane is between 400 g/m² and 4000 g/m², and is by preference between 1000 g/m² and 2500 g/m².

10 Needling or needle punching can be done by punching the web of metal fibres by means of a bed of needles. Due to this operation, the metal fibres are intertwined with one another, a fact which lends considerable mechanical cohesion and strength, yet does not impair the good deformability of the needled felt and yet does not lead to an unacceptable decrease in porosity.

15 During the needling operation care must be taken not to punch twice or more times at the same spot, since this may decrease the homogeneity of the web.

Moreover, the thermal expansion of the burner membrane can take place unhindered, and there is nearly no danger of cracks or fissures appearing.

20 A needled web of ceramic fibres for burners is known in the art, e.g. in US-A-5,024,596 (priority date : 1985). Needling of a web of ceramic fibres is done in order to avoid the use of a binder and to render the ceramic fibre web more pliable as a result of the avoiding of the binder. Having regard, however, to the brittleness of the ceramic fibres, the degree of compressing of a needled fibre web is
25 very limited

In order to improve the homogeneity of the gas flow even further, the burner membrane according to the invention can be perforated

in a regular pattern over at least a portion of its surface, for example by mechanical means or with the aid of laser techniques.

5 The web formation, needling, compressing and in some cases perforating can be carried out consecutively on a single production line, which makes the manufacture of the burner membrane relatively simple and inexpensive.

10 The burner membrane according to the invention can also be coated with substances that activate the oxidation of the fuel mixture.

15 In an alternative embodiment, the needled metal fibre web, whether multilayered or not, can be pressed in a cold isostatic manner such that a smooth surface is obtained on either one or both sides of the web. The principle of cold isostatic pressing is described in European patent EP 0329863 of the applicant.

20 Furthermore, in addition to a needled fibre web, another metal fibre network, such as a woven or knitted fabric, can also be incorporated into the burner membrane according to the invention.

Description of a preferred embodiment of the invention.

25 **Example**

A burner membrane according to the invention has been manufactured out of Fecralloy® heat-resistant stainless steel fibres having an equivalent diameter of 35 µm. Four metal fibre webs
30 were stacked on top of one another and needled to form a multi-

layered needled felt with a weight of 1580 g/m^2 . This needled felt was placed between two stainless steel plates and rolled at a pressure of 200 bar to form a membrane with a thickness of 1.5 mm and a nearly homogeneous porosity of 85.7%.

5

The (flat) burner membrane thus obtained was used as a part of a surface burner for gas, and was tested in a radiation system and a blue-flame system at heat fluxes of 100 to 5000 kW/m^2 .

10

The high, homogeneous porosity of the burner membrane results in a very homogeneous combustion and enables the use of large gas flows.

15

In addition, the burner membrane has good deformability and substantial mechanical sturdiness.

20

Moreover, as a result of the very open structure of the burner membrane, no filter is required for the gas mixture which is to be burned.

25

The chance of flame resonance is very small, so that, among other things, the disturbance of whistling sounds is avoided.

Furthermore, the burner membrane according to the invention offers good resistance to flashback, both with sub- and super-stoichiometric combustion of (for example) methane, ethane, propane and butane, or of gases containing hydrogen and/or carbon monoxide.

-7-

Moreover, the burner membrane according to the invention offers the advantage that the required time span for warming up or cooling off is extremely short, so that a very great variation in heat flux can be realized in a very short time (order of magnitude of seconds).

5 Hence the changeover from one combustion system to another occurs very smoothly and the cooling off time is very short. This quick response is very advantageous from the point of view of safety.

CLAIMS

1. Burner membrane comprising at least one layer consisting of a needed fibre web which is compressed and which has a porosity of between 60 % and 95 %, and that is constructed of heat-resistant stainless steel fibres.
5
2. Burner membrane according to Claim 1, in which the porosity of the needed fibre web is between 80 % and 95 %.
10
3. Burner membrane according to Claim 1, in which the fibre web consists of steel fibres having an equivalent diameter of between 5 μm and 150 μm .
4. Burner membrane according to Claim 3, in which the fibre web consists of steel fibres having an equivalent diameter of between 10 μm and 50 μm .
15
5. Burner membrane according to Claim 1, in which the weight of the fibre web is between 400 g/m^2 and 4000 g/m^2 .
20
6. Burner membrane according to Claim 5, in which the weight of the fibre web is between 1000 g/m^2 and 2500 g/m^2 .
7. Burner membrane according to Claim 1, which is provided with a regular pattern of perforations over at least a portion of its surface.
25

8. Burner membrane according to any one of the preceding claims, wherein said steel fibres are obtained by shaving the rolled edge of a roll of metal foil.

5 9. Method for manufacturing a burner membrane according to Claim 1 comprising the following steps:

- (a) providing a fibre web composed of metal fibres ;
- (b) needling the fibre web ;
- (c) compressing the needled fibre web to the desired porosity.

10

10. Method for avoiding a sintering operation in the manufacture of a burner membrane, said method comprising the following steps :

- (a) providing a fibre web composed of metal fibres ;
- (b) needling the fibre web ;
- (c) compressing the needled fibre web to the desired porosity.

15

11. Method according to claim 8 or 9 wherein the compressing of the needled fibre web is done to such a degree that cold weldings between the individual fibres are avoided.

20

12. Use of a burner membrane according to Claims 1 or 7 as part of a surface burner for gas.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 98/06245

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 F23D14/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 F23D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 024 596 A (SMITH THOMAS M) 18 June 1991 cited in the application see column 20, line 45 - column 23, line 17; figures 12-15.	1-7, 9, 12
Y	WO 97 04152 A (BEKAERT SA NV ;DEWAEGHENEIRE GABRIEL (BE); VANSTEENKISTE PHILIP (B) 6 February 1997 cited in the application see the whole document	1-6, 9, 12
Y	WO 93 18342 A (ACOTECH SA NV ;BEKAERT SA NV (BE)) 16 September 1993 cited in the application see the whole document	7
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

27 January 1999

Date of mailing of the international search report

03/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Coll. E

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 98/06245

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 380 580 A (ROGERS JOHN J ET AL) 10 January 1995 see column 1, line 62 - column 2, line 22 see column 3, line 56 - line 62; claims 1,7,22	1-7
A	EP 0 348 993 A (OSAKA GAS CO LTD) 3 January 1990 see the whole document	1-7
A	US 4 930 199 A (YANAGISAWA AKIRA) 5 June 1990 cited in the application see the whole document	8

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/06245

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5024596	A	18-06-1991	US 4290746 A	22-09-1981
			US 4272238 A	09-06-1981
			US 4830651 A	16-05-1989
			US 4373904 A	15-02-1983
			US 4378207 A	29-03-1983
			US 4447205 A	08-05-1984
			US 4035132 A	12-07-1977
			US 4604054 A	05-08-1986
			US 4272237 A	09-06-1981
			US 4722681 A	02-02-1988
			US 4326843 A	27-04-1982
			US 5090898 A	25-02-1992
			US 5145056 A	08-09-1992
			US 5306140 A	26-04-1984
			US 4416618 A	22-11-1983
			US 4443185 A	17-04-1988
			CA 1168568 A	05-06-1984
			DE 3042580 A	27-05-1981
			GB 2064096 A,B	10-06-1981
			GB 2133526 A,B	25-07-1984
			JP 56082312 A	06-07-1983
			US 5046944 A	10-09-1991
			US 4500283 A	19-02-1985
			US 4654000 A	31-03-1987
			JP 57182006 A	09-11-1982
			CA 1088412 A	28-10-1980
			DE 2714835 A	20-10-1977
			GB 1581648 A	17-12-1980
			JP 1249644 C	25-01-1985
			JP 52144831 A	02-12-1977
			JP 59026207 B	25-06-1984
			JP 59137712 A	07-08-1984
			JP 1412505 C	27-11-1987
			JP 60014006 A	24-01-1985
			JP 62019651 B	30-04-1987
			US 4589843 A	20-05-1986
			US 4157155 A	05-06-1979
			CA 1118678 A	23-02-1982
			CA 1157367 A	22-11-1981
WO 9704152	A	06-02-1997	BE 1009485 A	01-04-1997
			CN 1191001 A	19-08-1998
			EP 0839221 A	06-05-1998
WO 9318342	A	16-09-1993	BE 1005739 A	11-01-1994
			BE 1006201 A	07-06-1994
			AT 174681 T	15-01-1999
			BR 9306001 A	21-10-1997
			CA 2117605 A	16-09-1993
			EP 0628146 A	14-12-1994
			JP 7504266 T	11-05-1995
US 5380580	A	10-01-1995	CA 2152085 A	21-07-1994
			DE 69305096 D	31-10-1996
			DE 69305096 T	30-04-1997
			EP 0678128 A	25-10-1995
			JP 8505442 T	11-06-1996
			NO 952693 A	07-07-1995

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/EP 98/06245

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5380580 A		WO 9416134 A	21-07-1994
EP 0348993 A	03-01-1990	JP 2014139 A	18-01-1990
		JP 2580265 B	12-02-1997
		DE 68912665 D	10-03-1994
		DE 68912665 T	19-05-1994
		US 4996102 A	26-02-1991
US 4930199 A	05-06-1990	JP 1316137 A	21-12-1989
		CA 1320616 A	27-07-1993
		CN 1036352 A,B	18-10-1989
		DE 3880451 A	27-05-1993
		DE 3880451 T	25-11-1993
		EP 0319959 A	14-06-1989
		JP 1153231 A	15-06-1989